



# GP 17.40 SUP

Slightly alkaline powder for decontamination of surfaces, in ultrasonic processes.

## COMPATIBILITY:

- All metals
- Zamak
- Aluminium

## INGREDIENTS:

- Surfactants, phosphates
- Chelating agents
- Corrosion inhibitors

## PHYSICAL AND CHEMICAL DATA:

- pH (3%): 9.9
- Density: n.m.
- Surface tension: 27.9 mN/m

## INSTRUCTIONS FOR USE:

The optimum conditions for use are affected by the quality of the water used in the baths and the type and quantity of contaminants.

- Concentration: 5 to 20 g/L
- Temperature: 40 to 70°C (104 to 158°F)
- Time: 1 to 3 minutes

## PROCESS EXAMPLE:

### CLEANING

<b>GP 17.40 SUP</b>  Conc.: 30g/L Temp.: 60°C 140°F Time: 5 min	<b>TAP WATER RINSE</b>  Temp.: 15°C 59°F Time: 3 min	<b>DI WATER RINSE</b>  Temp.: 20°C 68°F Time: 3 min	<b>DI WATER RINSE</b>  Temp.: 20°C 68°F Time: 3 min	<b>HOT AIR DRYING</b>
--	--	---	---	-----------------------

US

## BENEFITS:

- Excellent surface preparation before vacuum deposition
- Emulsifies and dissolves grease
- Perfect wettability of the surface
- The product does not tarnish metals
- Finish without residue after drying

17/11/17

## STORAGE CONDITIONS:

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging.



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

