



# KORROSTOP 7000

Innovative formulation for the protection of steel that becomes sensitive after being cleaned in an aqueous medium, for storage.

## COMPATIBILITY:

- Ferrous and copper alloys

## INGREDIENTS:

- Surfactants, solvating agents
- his product does not contain complexing agents or phosphates

## PHYSICAL AND CHEMICAL DATA:

- pH concentration: 11.2
- Density : 1.018
- Surface tension: 31.4 mN/m


## INSTRUCTIONS FOR USE:

The baths must be prepared using de-mineralised water. Optimum conditions for use are also affected by the type and quantity of contaminants.


- Concentration: 3 to 20%
- Temperature: 20 to 60°C / 68 to 140°F
- Time: 1 to 5 minutes

## PROCESS EXAMPLES:

- Application:



- Removal:



## BENEFITS :

- Easily removed using alkaline washing medium
- Economical due to dilution between 3 and 20%
- Exceptional anti-corrosion power: through the creation of a thin semi-permanent transparent layer
- Allows for long-term storage of items sensitive to oxidation
- Applied by dipping or spraying at room temperature
- Not flammable

06/05/19

## STORAGE CONDITIONS:

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging.



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

